



SAITACK 514

Typical Physical Properties

Property	Value
Percent Solids	58.0
Polymer Type	Acrylic
Brookfield Viscosity @ 25°C LVT spindle #3 @ 12rpm	5,000 to 13,000 cps.
pH	8.5
Stabilization System	Anionic
Appearance (wet)	White
Odor	Slight Acrylic

Description

Pressure sensitive adhesive designed for use on expanded polymer foam tape.

Suggested Uses

- Expanded polymer tapes including polyurethane, PVC and polyethylene based foam tapes.

Characteristics

- High performance PSA for use on foam tape.
- High tack and peel adhesion on various substrates.
- Good heat resistance.
- APEO Free Product**

Sample Preparation

Substrate: 6mm Polyurethane Foam. Coating Thickness: 70 µm/dry;
Dry Condition: 100°C x 3 min.

Typical Performance Properties

90° Peel (N/25mm)	After 20 minutes	SS	2.5 lbs./in	According to JIS Z0237
		PP	2.2 lbs./in	
	After 24 hours	SS	2.1 lbs./in	According to JIS Z0237
		PP	2.2 lbs./in	
Shear (min)		SS	550	Press with 49N weight roller for 1-back/forth
		PP	500	Load: 4.9N Measuring Temperature: 23°C 50% RH
Softening point (°C)	SS	62	Press with 49N weight roller for 1-back-forth Load: 4.9N Elevating temperature: 3°C in 5 min	
	PP	59		
Curved surface (peeled / mm)	SS	10	Bar: 80 mm Ø	
	PP	22	After 80°C x 24 hours	
Constant load Peel (min)	SS	≥500	Press with 49N weight roller for 1-back-forth Load: 0.98N Measuring temperature: 23°C 50% RH	
	PP	≥500		



5618 Clyde Rhyne Drive
Sanford, NC 27330
Phone: 800-874-5878
Fax: 919-777-6695
stipolymer.com



SAITACK 514

Description

STI Polymer is the partner of choice for custom formulations and manufacturing of adhesives, paints and coatings. STI Polymer has built a reputation of proven performance, from providing manufacturers of paints and adhesives with the basic functional components of their formulations to producing private labeling of high-quality products for leading global corporations. STI's robust technical foundation and agility to meet the emerging needs, combined with an emphasis on long-term partnerships, drives its customer' successes.

STI Polymer

You drive. We navigate.

General Properties

Recommended Storage:

Protect from freezing. Recommended storage temperature is 60°F to 80°F (15°C to 25°C). Keep in tightly covered container.

Shelf Life:

Six months from date of manufacture.

Packaging:

One-way drums and totes or bulk shipments available.

DOT Label Required:

This product is not classified as a hazardous product under DOT or OSHA regulations. It does not contain any hazardous components at levels which have implications for labeling under these regulations.

Clean-up:

Soapy water (wet), Solvent (dry)

Material Safety Data Sheet:

Consult all information contained in the material Safety Data sheet for this product.

Because we cannot anticipate nor control the many different conditions under which this information and our products may be used, we do not guarantee the applicability or the accuracy of this information or the suitability of our products in any given situation. Users of our product should make their own tests to determine the suitability of each such product for their particular purposes. The products discussed are sold without warranty, either express or implied, and the buyer assumes all responsibility for loss or damage arising from the handling or use of our products, whether done in accordance with directions or not. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent.



5618 Clyde Rhyne Drive
Sanford, NC 27330
Phone: 800-874-5878
Fax: 919-777-6695
stipolymer.com