



Concrete Coating & Admixtures

Brookfield Viscosity														
Product	Description	Polymer	% Solids	Model	Spindle #	RPM's	CPS Range	pH	Tg (C°)	Particle Size (nm)	Lbs./ gallon	MFFT (C°)	Remarks	Self Cross-linking
Sycoat® 2020	Core-shell technology	Acrylic	41 to 43	LVT	62	12	500 to 1,500	8.6 to 9.2	46	99	8.8	3	Excellent anti-blush, superior weathering, silicone modified	X
Sycoat® UC-404	Penetrating topcoat.	Styrene Acrylic	48 to 50	LVT	62	12	500 to 2,000	8.0 to 9.0	14	134	8.5	29	Good blocking, fast dry time, great metal adhesion	O
Sycoat® 299	Penetrating concrete and architectural coatings	Styrene Acrylic	48 to 50	LVT	62	12	500 to 2,000	8.0 to 9.0	32	168	8.5	27	Good adhesion to a variety of surfaces including galvanized metals and concrete.	O
Sycoat® 520	Clear concrete coatings	Styrene Acrylic	43 to 45	LVT	62	12	<300	8.0 to 9.0	23	154	8.4	34	Excellent anti-blush and water resistance, great adhesion to concrete	X
Sycoat® 123	Masonry and Textured Coatings	Styrene Acrylic	48 to 50	LVT	62	12	300 to 700	8.0 to 9.0	25	153	8.7	19	Good cohesive strength ideal for textured coating formulas	O

STI Polymer
 5618 Clyde Rhyne Drive
 Sanford, NC 27330
 Phone: 800-874-5878
 Fax: 919-777-6695
 stipolymer.com



Concrete Coating & Admixtures

				Brookfield Viscosity										
Product	Description	Polymer	% Solids	Model	Spindle #	RPM's	CPS Range	pH	Tg (C°)	Particle Size (nm)	Lbs./gallon	MFFT (C°)	Remarks	Self Cross-linking
Sycoat® 223	Concrete coatings and additive for asphalt emulsions.	Styrene Acrylic	48 to 50	LVT	62	12	500 to 2,000	8.0 to 9.0	50	0.17	8.4	56	Good blocking, fast dry time, great metal adhesion	X
Sycoat® 822	Admixture for mortar and cement sand mixtures.	Styrene Acrylic	49 to 50	LVT	62	12	200 to 1,000	8.0 to 9.0	4	162	8.7	0	Good flexibility for coatings and admixture	X

Description

STI Polymer is the partner of choice for your custom formulations of adhesives, paints and coatings. STI Polymer has built a reputation of proven performance, from providing manufacturers of paints and adhesives with the basic functional components of their formulations to producing private labeling of high-quality products for leading global corporations. STI's robust technical foundation and agility to meet the emerging needs, combined with an emphasis on long-term partnerships, drives its customers' successes.

STI Polymer

You drive. We navigate.

Because we cannot anticipate nor control the many different conditions under which this information and our products may be used, we do not guarantee the applicability or the accuracy of this information or the suitability of our products in any given situation. Users of our product should make their own tests to determine the suitability of each such product for their particular purposes. The products discussed are sold without warranty, either express or implied, and the buyer assumes all responsibility for loss or damage arising from the handling or use of our products, whether done in accordance with directions or not. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent.

STI Polymer
5618 Clyde Rhyne Drive
Sanford, NC 27330
Phone: 800-874-5878
Fax: 919-777-6695
stipolymer.com