

Direct to Metal (DTM)

Brookfield Viscosity

Product	Description	Polymer	% Solids	Model	Spindle #	RPM's	CPS Range	pH	Tg (C°)	Particle Size (nm)	Lbs./gallon	MFFT (C°)	Remarks	Self Cross-linking
Sycoat® 223	Admixture for asphalt emulsions needing adhesion to metal surfaces.	Styrene Acrylic	48 to 50	LVT	62	12	500 to 2,000	8.0 to 9.0	50	133	8.4	54	Good blocking, fast dry time, great metal adhesion	O
Sycoat® UC-404	Great base for industrial maintenance coatings	Styrene Acrylic	48 to 50	LVT	62	12	500 to 2,000	8.0 to 9.0	14	140	8.5	29	Good blocking, fast dry time, great metal adhesion	O
Sycoat® 263	Acrylic emulsion for railcar paints.	Acrylic	46.5 to 48.5	LVT	62	12	150 to 650	7.0 to 8.0	26	95	8.7	26	Fast drying, good water resistance, good flexibility	O
Sycoat® 273	Industrial Primers & Coatings	Styrene Acrylic	47.5 to 49.5	LVT	62	12	300 to 3,000	8.0 to 9.0	28	240	8.8	28	Good early water, hardness, and corrosion resistance	O



Direct to Metal (DTM)

Description

STI Polymer is the partner of choice for your custom formulations of adhesives, paints and coatings. STI Polymer has built a reputation of proven performance, from providing manufacturers of paints and adhesives with the basic functional components of their formulations to producing private labeling of high-quality products for leading global corporations. STI's robust technical foundation and agility to meet the emerging needs, combined with an emphasis on long-term partnerships, drives its customers' successes.

STI Polymer

You drive. We navigate.

Because we cannot anticipate nor control the many different conditions under which this information and our products may be used, we do not guarantee the applicability or the accuracy of this information or the suitability of our products in any given situation. Users of our product should make their own tests to determine the suitability of each such product for their particular purposes. The products discussed are sold without warranty, either express or implied, and the buyer assumes all responsibility for loss or damage arising from the handling or use of our products, whether done in accordance with directions or not. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent.