



# SYCOAT<sup>®</sup> 700

## Typical Physical Properties

### Description

Styrene Acrylic Emulsion

### Suggested Uses

- Elastomeric roof primer, coating base polymer

### Characteristics

- Provides excellent resistance to asphalt bleed-through, ponding water, UV exposure and dirt pick-up when properly formulated and applied.
- Primarily suitable for moderate climates.

Property	Value
Percent Solids	48.5 to 50.5
Polymer Type	Styrene Acrylic
Brookfield Viscosity @ 25°C LVT #63 @ 12 rpm (cps.)	5,000 to 8,000
pH	8.0 to 9.0
Tg (°C)	29
MFFT (°C)	17
Density lbs./gallon @ 25 °C	8.7
Particle Size (nm)	155
Permeability (perms)	1.5
Dispersion Type	Anionic
Appearance (wet)	Milky White
Odor	Slight Acrylic



5618 Clyde Rhyne Drive  
Sanford, NC 27330  
Phone: 800-874-5878  
Fax: 919-777-6695  
stipolymer.com



# SYCOAT® 700

## Description

STI Polymer is the partner of choice for custom formulations and manufacturing of adhesives, paints and coatings. STI Polymer has built a reputation of proven performance, from providing manufacturers of paints and adhesives with the basic functional components of their formulations to producing private labeling of high-quality products for leading global corporations. STI's robust technical foundation and agility to meet the emerging needs, combined with an emphasis on long-term partnerships, drives its customer' successes.

## STI Polymer

You drive. We navigate.

## General Properties

### Recommended Storage:

Protect from freezing. Recommended storage temperature is 60°F to 80°F (15°C to 25°C). Keep in tightly covered container.

### Shelf Life:

Six months from date of manufacture.

### Packaging:

One-way drums and totes or bulk shipments available.

### DOT Label Required:

This product is not classified as a hazardous product under DOT or OSHA regulations. It does not contain any hazardous components at levels which have implications for labeling under these regulations.

### Clean-up:

Soapy water (wet), Solvent (dry)

### Material Safety Data Sheet:

Consult all information contained in the material Safety Data sheet for this product.

Because we cannot anticipate nor control the many different conditions under which this information and our products may be used, we do not guarantee the applicability or the accuracy of this information or the suitability of our products in any given situation. Users of our product should make their own tests to determine the suitability of each such product for their particular purposes. The products discussed are sold without warranty, either express or implied, and the buyer assumes all responsibility for loss or damage arising from the handling or use of our products, whether done in accordance with directions or not. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent.



5618 Clyde Rhyne Drive  
Sanford, NC 27330  
Phone: 800-874-5878  
Fax: 919-777-6695  
stipolymer.com