

White Roof Coatings

				Brookfield Viscosity										
Product	Description	Polymer	% Solids	Model	Spindle #	RPM's	CPS Range	pH	Tg (C°)	Particle Size (nm)	Lbs./gallon	MFFT (C°)	Remarks	Self Cross-linking
Sycoat® 7626	Pure acrylic emulsion for premium coatings for all roofing substrates.	Acrylic	54 to 56	RVT	3	20	<2,500	8.0 to 9.0	-4	100	8.5	≤0	Excellent water resistance with low water absorption. Excellent flexibility at low temperatures with UV stability.	No
Sycoat® 29	Purse acrylic emulsion for premium coatings.	Acrylic	54 to 56	LVT	62	12	300 to 900	8.0 to 9.0	-22	180	8.6	≤0	Superior dirt pick-up resistance; adheres to many substrates.	No
Sycoat® 7649	Syrene acrylic emulsion for moderate climate coatings.	Styrene Acrylic	54 to 56	LVT	62	12	200 to 1,000	8.0 to 9.0	0	210	8.7	≤0	Exceptional elongation and tear resistant properties with good dirt pick up resistance.	No
Sycoat® 700	Styrene acrylic emulsion for "base coats" used to hide asphalt bleed through.	Styrene Acrylic	48.5 to 50.5	LVT	63	12	5,000 to 8,000	8.0 to 9.0	29	155	8.7	17	Hides asphalt bleed through, good ponding water, good DPR	No



White Roof Coatings

				Brookfield Viscosity										
Product	Description	Polymer	% Solids	Model	Spindle #	RPM's	CPS Range	pH	Tg (C°)	Particle Size (nm)	Lbs./gallon	MFFT (C°)	Remarks	Self Cross-linking
Sycoat® 166	All acrylic emulsion.	Acrylonitrile Acrylic	57 to 59	LVT	61	12	100 to 300	5.0 to 7.0	-10	220	8.5	≤0	Great flexibility with high binding capacity.	No

Description

STI Polymer is the partner of choice for your custom formulations of adhesives, paints and coatings. STI Polymer has built a reputation of proven performance, from providing manufacturers of paints and adhesives with the basic functional components of their formulations to producing private labeling of high-quality products for leading global corporations. STI's robust technical foundation and agility to meet the emerging needs, combined with an emphasis on long-term partnerships, drives its customers' successes.

STI Polymer

You drive. We navigate.

Because we cannot anticipate nor control the many different conditions under which this information and our products may be used, we do not guarantee the applicability or the accuracy of this information or the suitability of our products in any given situation. Users of our product should make their own tests to determine the suitability of each such product for their particular purposes. The products discussed are sold without warranty, either express or implied, and the buyer assumes all responsibility for loss or damage arising from the handling or use of our products, whether done in accordance with directions or not. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent.

STI Polymer
5618 Clyde Rhyne Drive
Sanford, NC 27330
Phone: 800-874-5878
Fax: 919-777-6695
stipolymer.com