

SAITACK® 3550

Description

Vinyl Acrylic Emulsion

Suggested Uses

 Formulating Base for compounded adhesives and film to craft laminating

Characteristics

- Extremely aggressive dry tack
- Good green strength

Typical Physical Properties

Property	Value
Percent Solids	51 to 54
Polymer Type	Vinyl Acrylic
Brookfield Viscosity @ 25°RVT #3 @ 20rpm (cps.)	250 to 1,250
рН	4.0 to 7.0
Tg (°C)	-35
Density (lbs./gallon @ 25°C)	8.4
Dispersion Type	Anionic
Appearance (wet)	MilkyWhite
Film Appearance(dry)	Clear
Odor	Slight Acrylic

Typical Performance Properties

Property	Value
Peel Adhesion 180° (stainless steel / 1 mil. PET, 1 mil. Dry, 20 min. dwell)	2,000 (g/25mm) 4.4 (lb./in.)
Static Shear (1'x1'x1kg @ 25°C)	35 (min)
Loop Tack	25 (oz.) 1.6 (lb.)
Water Resistance	Excellent



5618Clyde Rhyne Drive Sanford,NC 27330 Phone: 800-874-5878 Fax: 919-777-6695 stipolymer.com



SAITACK® 3550

Description

STI Polymer is the partner of choice for custom formulations and manufacturing of adhesives, paints and coatings. STI Polymer has built a reputation of proven performance, from providing manufacturers of paintsand adhesives with the basic functional components of their formulations to producing private labelingof high-quality products for leading global corporations. STI's robust technical foundation and agility to meet the emerging needs, combinedwith an emphasis on long-term partnerships, drives its customer' successes.

STI Polymer

You drive. We navigate.

General Properties

Recommended Storage:

Protect from freezing. Recommended storage temperature is 60°F to 80°F (15°C to 25°C). Keep in tightly covered container.

Shelf Life:

Six months from date of manufacture.

Packaging:

One-way drums and totes or bulk shipments available.

DOT Label Required:

This product is not classified as a hazardous product under DOT or OSHA regulations. It does not contain any hazardous components at levels which have implications for labeling under these regulations.

Clean-up:

Soapy water (wet), Solvent (dry)

Material SafetyData Sheet:

Consult all information contained in the material Safety Data sheet for this product.

Because we cannot anticipate nor control the many different conditions under which this information and our products may be used, we do not guarantee the applicability or the accuracy of this information or the suitability of our products in any given situation. Users of our product should make their own tests to determine the suitability of each such product for their particular purposes. The products discussed are sold without warranty, either express or implied, and the buyer assumes all responsibility for loss or damage arising from the handling or use of our products, whether done in accordance with directions or not. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent.