



Adhesive Compounding

Product	Polymer	Description	Solids (%)	Viscosity (cps)	pH	Tg (°C)	Suggested Uses
Saitack® 463	Acrylonitrile Acrylic	Great PSA for water-based PVC bonding adhesive	60 to 62	250 to 1,250	6.0 to 7.0	-31	Acrylic copolymer containing acrylonitrile.
Saitack® 3550	Vinyl Acrylic	High tack EPDM and film laminating bonding adhesive	51 to 54	1,200 to 2,300	4.0 to 7.0	-35	Formulating base for compounded adhesives and film to craft laminating.
Saitack® 970	Acrylic	Base for high solids PSAs.	69 to 71	<1,000	5.0 to 6.0	-44	Formulating base ideally suited for vinyl flooring adhesives, PSA, and packaging adhesives.
Saitack® 934	Acrylic	High solids PSA for film lamination.	68 to 70	4,000 to 7,000	3.5 to 4.5	-46	Formulating base for pressure sensitive and film laminating adhesives.
Saitack® 935	Vinyl Acrylic	High solids pressure sensitive polymer for construction adhesives.	68 to 70	2,000 to 4,000	4.0 to 6.0	-48	Formulating base for pressure sensitive and film laminating adhesives.
Saitack® 269	Acrylic	High solids pressure sensitive for EPDM adhesives.	66 to 68	3,000 to 4,000	7.5 to 8.5	-42	Excellent foundation for rubber or rubber backed flooring surfaces. PSA for bonding single-ply roofing membranes. Great water resistance.
Saitack® 400	Acrylonitrile Acrylic	Pressure sensitive polymer for wood flooring adhesives.	60 to 61.5	2,000 to 3,000	5.0 to 5.5	-47	Base polymer emulsion for compounded construction adhesives, pressure sensitives and sealants.



Adhesive Compounding

Product	Polymer	Description	Solids (%)	Viscosity (cps)	pH	Tg (°C)	Suggested Uses
Saitack® 307	Acrylonitrile Acrylic	Pressure sensitive polymer for luxury flooring surfaces.	64 to 66	200 to 1,500	4.0 to 5.0	-35	Formulating base for construction adhesives, flooring/carpet adhesives and sealants.
Saitack® 426	Acrylonitrile Acrylic	Tackifier PSA for construction adhesives. Great water bonding adhesive for TPO.	59 to 61	2,000 to 4,000	7.5 to 8.5	-40	Bonding adhesive for attaching single-ply TPO and EPDM roofing membranes.
Saitack® 926	Vinyl Acrylic	PSA emulsion for construction adhesives.	59 to 61	2,000 to 3,000	7.0 to 9.0	-40	Formulating base for compounded PSAs. Filmic label.

Description

STI Polymer is the partner of choice for your custom formulations of adhesives, paints and coatings. STI Polymer has built a reputation of proven performance, from providing manufacturers of paints and adhesives with the basic functional components of their formulations to producing private labeling of high-quality products for leading global corporations. STI's robust technical foundation and agility to meet the emerging needs, combined with an emphasis on long-term partnerships, drives its customers' successes.

STI Polymer

You drive. We navigate.

Because we cannot anticipate nor control the many different conditions under which this information and our products may be used, we do not guarantee the applicability or the accuracy of this information or the suitability of our products in any given situation. Users of our product should make their own tests to determine the suitability of each such product for their particular purposes. The products discussed are sold without warranty, either express or implied, and the buyer assumes all responsibility for loss or damage arising from the handling or use of our products, whether done in accordance with directions or not. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent.

STI Polymer
 5618 Clyde Rhyne Drive
 Sanford, NC 27330
 Phone: 800-874-5878
 Fax: 919-777-6695
 stipolymer.com