

WHITE ROOF COATINGS

Typical Physical and Performance Properties

Property	Sycoat® EC-064	Sycoat® 29	Sycoat® 166	Sycoat® 7648	Sycoat® 7626	Sycoat® 7649	Sycoat® 84
Percent Solids	50	55	58	55	55	55	55
Polymer	Acrylic	Acrylic	Acrylonitrile Acrylic	Styrene Acrylic	Acrylic	Styrene Acrylic	Styrene Acrylic
Viscosity @ 25°C (cps.)	300 - 600	300 - 900	100 - 300	200 - 1,000	≤2,500	200 - 1,000	200 - 1,000
pH	8.0	8.5	6.0	8.5	8.5	8.5	8.5
Tg (°C)	-35	-22	-10	-10	-4	0	0
Density (lbs./gallon) @ 25°C	8.5	8.6	8.8	8.7	8.5	8.7	8.7
Particle Size (nm)	170	180	220	230	100	210	190
Dispersion Type	Anionic	Anionic	Anionic	Anionic	Anionic	Anionic	Anionic
APEO Free	No	Yes	No	Yes	Yes	Yes	Yes
Self-Cleaning	No	No	No	Yes	Yes	Yes	No

SHINE BRIGHT, STAY CLEAN

DISCOVER THE WONDERS OF SELF-CLEANING
WHITE ROOF POLYMERS NEWEST TECHNOLOGY