



# SAITACK 269

## Extremely “clean” Acrylic Emulsion Technology

### Description

High Solids Acrylic Emulsion

### Suggested Uses

- Excellent foundation for rubber flooring and rubber backed flooring surfaces
- Premium pressure sensitive adhesive for bonding single-ply roofing membranes

### Characteristics

- Great adhesion to a wide variety of flooring substrates
- Fast drying
- Superior tack, adhesion and plasticizer resistance
- Excellent water resistance when properly formulated and applied
- **APEO Free Product**

\*Stainless Steel to PET preparation:  
Drying conditions: 3 minutes @120°C  
Coating: 1 mil, machine roll coated  
Condition: 16 Hour Peel

## Typical Physical Properties

Property	Value
Percent Solids	66 to 68
Polymer Type	Acrylic
Brookfield Viscosity @ 25°C RVT #4 @ 20 rpm (cps.)	3,000 to 4,000
pH	7.5 to 8.5
Tg (°C)	-42
MFFT (°C)	≤0
Density lbs./gallon @ 25° C	8.6
Dispersion Type	Anionic
Appearance (wet)	Milky White
Film Appearance (dry)	Clear
Odor	Slight Acrylic

## Typical Performance Properties

Property	Value
Peel Adhesion 180° (stainless steel / 1 mil. PET, 1 mil. Dry, 20 min. dwell) (g/25mm)	>350
Static Shear (1'x1'x1kg @40°C) (min)	>1,440



5618 Clyde Rhyne Drive  
Sanford, NC 27330  
Phone: 800-874-5878  
Fax: 919-777-6695  
stipolymer.com

Exhibits great results in  
**GREENGUARD**  
chamber type testing

1 of 2  
©STI Polymer  
REV 16 July 11. 2023



# SAITACK 269

## Description

STI Polymer is the partner of choice for custom formulations and manufacturing of adhesives, paints and coatings. STI Polymer has built a reputation of proven performance, from providing manufacturers of paints and adhesives with the basic functional components of their formulations to producing private labeling of high-quality products for leading global corporations. STI's robust technical foundation and agility to meet the emerging needs, combined with an emphasis on long-term partnerships, drives its customer' successes.

## STI Polymer

You drive. We navigate.

## General Properties

### Recommended Storage:

Protect from freezing. Recommended storage temperature is 60°F to 80°F (15°C to 25°C). Keep in tightly covered container.

### Shelf Life:

Six months from date of manufacture.

### Packaging:

One-way drums and totes or bulk shipments available.

### DOT Label Required:

This product is not classified as a hazardous product under DOT or OSHA regulations. It does not contain any hazardous components at levels which have implications for labeling under these regulations.

### Clean-up:

Soapy water (wet), Solvent (dry)

### Material Safety Data Sheet:

Consult all information contained in the material Safety Data sheet for this product.

Because we cannot anticipate nor control the many different conditions under which this information and our products may be used, we do not guarantee the applicability or the accuracy of this information or the suitability of our products in any given situation. Users of our product should make their own tests to determine the suitability of each such product for their particular purposes. The products discussed are sold without warranty, either express or implied, and the buyer assumes all responsibility for loss or damage arising from the handling or use of our products, whether done in accordance with directions or not. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent.



5618 Clyde Rhyne Drive  
Sanford, NC 27330  
Phone: 800-874-5878  
Fax: 919-777-6695  
stipolymer.com